

FORM PTO-1390
(REV 11-98)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

017769-000400US

U.S. APPLICATION NO. (If known, see 37 CFR 1.51)

09/700157

INTERNATIONAL APPLICATION NO.
PCT/EP99/03261INTERNATIONAL FILING DATE
May 8, 1999PRIORITY DATE CLAIMED
May 12, 1998TITLE OF INVENTION
PRIMARY OR SECONDARY ELECTROCHEMICAL GENERATOR

APPLICANT(S) FOR DO/EO/US

MICHEL GRAETZEL; FRANCOIS R. SUGNAUX; NICOLAS PAPPAS

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☒ Other items or information:
ISR, 4 references

- 17.
- ☒
- The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)):

Neither international preliminary examination fee (37 CFR 1.482)
nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO
and International Search Report not prepared by the EPO or JPO \$970.00

International preliminary examination fee (37 CFR 1.482) not paid to
USPTO but International Search Report prepared by the EPO or JPO \$840.00

International preliminary examination fee (37 CFR 1.482) not paid to USPTO but
international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$760.00

International preliminary examination fee paid to USPTO (37 CFR 1.482)
but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$670.00

International preliminary examination fee paid to USPTO (37 CFR 1.482)
and all claims satisfied provisions of PCT Article 33(1)-(4) \$96.00

CALCULATIONS PTO USE ONLY

ENTER APPROPRIATE BASIC FEE AMOUNT = \$ 860

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(e)).

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	16 - 20 =		X \$18.00
Independent claims	1 - 3 =		X \$78.00

MULTIPLE DEPENDENT CLAIM(S) (if applicable) + \$260.00

TOTAL OF ABOVE CALCULATIONS = \$860

Reduction of 1/2 for filing by small entity, if applicable. A Small Entity Statement
must also be filed (Note 37 CFR 1.9, 1.27, 1.28).

SUBTOTAL = \$

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(f)).

TOTAL NATIONAL FEE = \$860

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +

TOTAL FEES ENCLOSED = \$ 860

Amount to be:	\$
refunded	
charged	\$

- a. ☐ A check in the amount of \$_____ to cover the above fees is enclosed.
- b. ☒ Please charge my Deposit Account No. 20-1430 in the amount of \$ 860 to cover the above fees.
A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
overpayment to Deposit Account No. 20-1430. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

J. Georg Seka
Townsend and Townsend and Crew LLP
Two Embarcadero Center, 8th fl.
San Francisco, CA 94111

SIGNATURE

Kevin T. LeMond

NAME

35,933

REGISTRATION NUMBER

09/700157

526 Rec'd PCT/PTO 10 NOV 2000 PATENT
Attorney Docket No.: 17769-000400US
Client Reference No.: XOLOX 01 PCT
US

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re U.S. National Phase of
PCT/EP99/03261 of:

MICHAEL GRAETZEL, et al.

Application No.: Not yet assigned

Filed: Herewith

For: PRIMARY OR SECONDARY
ELECTROCHEMICAL GENERATOR

PRELIMINARY AMENDMENT

San Francisco, CA 94111
November 10, 2000

Box PCT
Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Prior to examination of the above-referenced application, please enter the following amendments and remarks.

IN THE CLAIMS:

Claim 3, line 1, please delete "or 2".

Claim 4, line 1, delete "any of claims 1 to 3" and substitute therefor

--claim 1--.

Claim 5, line 1, delete "any of claims 1 to 4" and substitute therefor

--claim 1--.

Claim 6, line 1, delete "any of claims 1 to 5" and substitute therefor

--claim 1--.

Claim 7, line 1, delete "any of claims 1 to 6" and substitute therefor

--claim 1--.

Claim 8, line 1, delete "any of claims 1 to 8" and substitute therefor

--claim 1--.

Claim 9, line 1, delete "any of claims 1 to 5 or 7 to 8" and substitute therefor
--claim 1--.

Claim 10, line 1, delete "any of claims 1 to 9" and substitute therefor
--claim 1--.

Claim 11, line 1, delete "any of claims 1 to 10" and substitute therefor
--claim 1--.

Claim 12, line 1, delete "any of claims 1 to 11" and substitute therefor
--claim 1--.

Claim 13, line 1, delete "any of claims 1 to 12" and substitute therefor
--claim 1--.

Claim 14, line 1, delete "any of claims 1 to 13" and substitute therefor
--claim 1--.

Claim 15, line 1, delete "any of claims 1 to 14" and substitute therefor
--claim 1--.

Claim 16, line 1, delete "any of claims 1 to 12 or 14 to 15, and claim 13" and
substitute therefor --claim 1--.


IN THE ABSTRACT:

Following the Abstract, delete "(FIG 1)".

REMARKS

Amendment is made to delete a minor informality in the Abstract, and to
eliminate all multiple dependencies from the claims, thereby avoiding the need to pay the
multiple dependent surcharge.

Respectfully submitted,



Kevin T. LeMond
Reg. No. 35,933

11/PRTS

09/700157

526 Rec'd PCT/PTO 10 NOV 2000

5

XOLOX 01 PCT / HM

PRIMARY OR SECONDARY ELECTROCHEMICAL GENERATOR

10 FIELD OF THE INVENTION

The invention relates to a high power density primary or secondary generator and, more specifically a generator in which at least one electrode is composed of a solid material characterized by a mesoscopic morphology. An electrolyte is present in the mesoporous network of said electrode forming a bicontinuous junction of very large surface area with the electroactive solid.

The invention also relates to an electrode of this type having a large ion exchange capacity and high electric power density that makes it particularly suited for application as a cathode or anode in a primary or secondary electrochemical generator, such as a lithium ion battery.

The invention also relates to processes for obtaining an electrode of this type involving sol gel precipitation and subsequent baking of the electrically active solid material. It discloses methods to produce the specific mesoporous morphology of the electrode, required for optimal performance of the electrochemical generator. More specifically, it discloses the use of surfactant assemblies as templates to induce the desired electrode texture during the formation of the electro-active solid.

To enhance the performance of the electrochemical generator, in particular with respect to its energy density and power density, all its constituent elements, in particular the electrode materials, the current collector, as well as the separator and the composition of the electrolyte have been scrutinized to allow for the judicious selection of the optimal combination of said constituents. The physical configuration of the generator elements, notably the effect of electrode and spacer thickness and porosity as well as their conformation has been examined.

10 DESCRIPTION OF PRIOR ART

European patent application EP 0 709 906 A1 discloses a positive electrode composed of a sintered mass of lithium compound oxide, the mean particle size of the electrically active powder being 33 μm . The particles are pressed into pellets of 1.5 mm size by applying high pressure with simultaneous baking at 350 to 700 °C. They report an improvement in the resistivity when baking at the elevated temperature presumably due to a degree of sintering within the active mass, thus improving somewhat the connectivity in the active material.

U.S. Pat. No. 5,604,057 discloses a cathode comprising amorphous microporous, sub-micron-size, lithium intercalateable manganese oxide having an internal surface area greater than about 100 m^2/g . Electrodes are fabricated by mixing the oxide with a binder, containing optionally a conducting polymer and heating the composite material at a temperature up to 400 °C. The temperature is limited to this value to prevent crystallization of manganese oxide. The high surface area and the amorphous nature of the active material structure proposed seem to increase the initial capacity of fabricated electrodes but the connectivity is hindered. Interior connectivity of the particles is poor and therefore requires a binder and/or a conducting binder within the electrode fabrication mixture. Another drawback in electrode construction with the amorphous material is that the exposure to temperatures can alter its structure by crystallization, limiting the reported benefits arising from its amorphous structure.

U.S. Pat.No. 5,211,933 and 5,674,644 disclose a method for the low temperature preparation of the spinel LiMn_2O_4 and layered LiCoO_2 phases prepared at temperatures less than 400°C using acetate precursors. The LiMn_2O_4 powder obtained comprises grains or crystallites ranging in size
5 between $0.3\ \mu\text{m}$ and $1\ \mu\text{m}$. Pellets are pressed containing this powder and about 10% carbon black and used as positive electrodes in lithium ion batteries. The particle sizes claimed are large to suit high rate discharge electrodes and connectivity within the active material particles is not ensured by special bonding, the conductivity enhanced by mixing in carbon powder to the active
10 powder.

U.S. Pat. No. 5,700,442 discloses insertion compounds based on manganese oxide usable as positive electrode active material in a lithium battery, prepared by reacting $\beta\text{-MnO}_2$ powder with a lithium compound at 150 to 500°C for an adequate time to convert these solid precursors to a spinel type. The specific
15 surface of the resulting powder is below $7\ \text{m}^2/\text{g}$. The large particle sizes, as deduced from the low specific surface area claimed here are not suited for high rate discharge electrodes.

European patent application EP 0 814 524 A1 discloses a spinel-type lithium manganese complex oxide for a cathode active material of a lithium ion
20 secondary battery. The average particle diameter is between 1 and $5\ \mu\text{m}$ and the specific surface area between 2 and $10\ \text{m}^2/\text{g}$. The large particle sizes, thus the low specific surface areas claimed here, are not optimum for high rate discharge electrodes.

25 BRIEF SUMMARY OF THE INVENTION

As compared to these known features of the prior art, the invention provides and electrochemical generator in which at least one electrode consists of a
30 mesoscopic, bicontinuous structure, composed of an interconnected solid material and of an interconnected network of mesopores. The electrically active solid is employed as a host for accommodating ions by an insertion process. At the same time, it serves to sustain the flow of electric current during charging

and discharging of the battery. Said electrically active solid is in contact with an interconnected porous space filled with electrolyte, the latter serving for ionic transport. Said electrode is characterized by the presence of an extremely large interface between the solid and the electrolyte, comprised between 10 and 5 3000 m²/g electrode material, permitting rapid exchange of ions between the solid and liquid phase. The architecture of the solid phase is designed to overcome the impediment of ionic diffusion in the electrolyte encountered with conventional high surface area electrodes. The specific three dimensional structure of the electrode disclosed by the invention ascertains interconnectivity 10 and mechanical stability of the solid phase providing ease of access of the electrolyte to the entire pore space. Furthermore, it renders possible the conduction of electric current within the solid even in the absence of conductive binders which are mixed with the electrically active material in conventional batteries to enhance electronic conductivity of the electrode. The electrically 15 active material in the form of such a mesoscopic morphology is obtained, for example, by employing surfactant assemblies exerting a templating effect during the formation of the solid from water-soluble precursor compounds or by sol-gel synthesis of a xerogel and subsequent sintering under appropriate conditions.

BRIEF DESCRIPTION OF THE INVENTION

Electrodes of lithium manganate, LiMn₂O₄ serving as cathode in the electrochemical generator are prepared by casting an aqueous mixture of the manganate precursor by the doctor blading technique or by screen printing or 25 dip coating of the substrate. The gel precursor is precipitated starting from homogeneous solutions of manganous diacetate or manganous diacetylacetonate at 0.13 M and LiOH at 1.3 M. The [Li]/[Mn³⁺] ratio equals to 10 for each precipitation reaction. The reaction temperature is fixed at 110°C and the pH of the reactants is increased to basic values (~12-13) using the 30 concentrated LiOH solution. In each experiment, the manganous salt solution and the LiOH solution are separately dissolved, before mixing them in a batch reactor with agitation. The reaction time is 2 hours after which the hydrolytic

reaction between LiOH and the manganate salt is terminated by rapidly cooling the solution to less than 10°C in an ice bath.

The gel it is applied in concentrated form to the substrate. Its consistency is controlled by the proportion of water in the mixture and the effectiveness of ambient drying of the cast layer. Each layer provides 0-3 µm (microns) of the dry precursor in porous form. This process is repeated to build up layers of many µm (microns). After deposition of the precursor, the film is heated at 700-750 °C in air with a temperature gradient of 5-10 °C/min. and few minutes rest at peak temperature. Figure 2 present the morphology of the electrode obtained by scanning electron microscopy.

An electrode of this type having in its composition an electroactive material in the form of a mesoscopic morphology provides a high energy storage capacity and high power density and may be used in both primary and secondary electrochemical generators. The electrolyte used in such a generator is preferably one containing protons or lithium ions. Other alkali or alkaline earth metals may also be used. According to a preferred embodiment, the electrolyte contains lithium ions brought into the form of one of its salts such as tetrafluoroborate, hexafluorophosphate, hexafluoroantimonate, hexafluoroarsenate, trifluoromethane sulfonate, bis (trifluorosulfonyl) imide, tris (trifluorosulfonyl) methide, trifluoromethanesulfonate, trifluoroacetate, tertachloroaluminate or perfluorobutane sulfonate. According to the preferred embodiment, the solvent of the electrolyte is an aprotic solvent or a liquid salt, such as ethylene carbonate, propylene carbonate, dimethylcarbonate diethylcarbonate, dioxolane, butyrolactone, methoxypropionitrile, methoxyethoxy propionitrile, methoxy-diethoxypropionitrile, methoxyacetonitrile, tetrafluoro-propanol or mixtures of these solvents. Another preferred embodiment of the invention uses a molten salt as a solvent for the lithium ion containing salt, such as methyl-ethyl-imidazolium trifluoromethanesulfonate or methy-ethyl-imidazolium bis (trifluorosulfonyl) imide and corresponding dimethyl-ethyl-imidazolium salts with the above anions. The material used for at least one electrode in form of a mesoporous layer may be an electrically active material, but according to the preferred embodiment, this material is chosen so as to form an insertion compound with alkali or alkaline earth metals, thereby

providing a secondary electrochemical generator. An electrically active material of this type will be chosen for example from the oxides or chalcogenides of transition metals or their lithiated or partially lithiated forms, such as TiO_2 , Nb_2O_5 , WO_3 , MoO_3 , MnO_2 , $\text{Li}_y\text{Mn}_2\text{O}_4$, HfO_2 , TiS_2 , WS_2 , TiSe_2 ,

- 5 Li_yNiO_2 , Li_yCoO_2 , $\text{Li}_y(\text{NiCo})\text{O}_2$, or Sn_yO_2 . According to the preferred embodiment of the invention, an electrode, which may be the cathode or the anode, depending on the electrical activity of the electrode used as the counterelectrode, is composed of mesoporous titanium dioxide in the form of anatase or in the form of a mixture of rutile and anatase, containing more than
- 10 50% anatase. In the presence of lithium ions, the titanium dioxide in mesoporous form is prone to form an intercalation compound Li_xTiO_2 in which the intercalation coefficient has a high value between 0.6 and 0.8. For a cell in which $x = 0.8$ and where the counterelectrode is made of lithium metal, the theoretical energy density is 400 Wh kg^{-1} assuming a mean value of the cell
- 15 voltage of 1.5 V. This high capacity is associated with a high value for the specific power, the later reaching values of 2.3 kW/kg . Results of this kind can not be obtained with the technologies of the prior art, such as described by W.J. Macklin et al. (Solid state Ionics 53 -56 (1992) 694-700) in which both the specific power and capacity of a conventional TiO_2 electrode is significantly
- 20 lower.

- When an electrically active compound also capable of inserting lithium ions is used for the other electrode, the electrochemical generator of the invention is a secondary (rechargeable) generator of the "rocking chair" type, the principles of which was described for the first time by M. Armand (Materials for Advanced
- 25 Batteries, D.W. Murph et al. ed. Plenum press N.Y. 1980, p145). According to a preferred embodiment of the invention, the rocking chair configuration employs TiO_2 in the anatase structure as anode material, while $\text{Li}_y\text{Mn}_2\text{O}_4$ in amorphous or crystalline form is used for the cathode. The $\text{Li}_y\text{Mn}_2\text{O}_4$ ($y \leq 2$) material disclosed by the invention is also present in the form of a mesoporous
 - 30 morphology, yielding cathodes of high capacity, i.e. close to the theoretical maximum of 280 Ah kg^{-1} . The overall capacity of such a $\text{TiO}_2/\text{Li}_y\text{Mn}_2\text{O}_4$ rocking chair battery reaches up to 140 Ah kg^{-1} , the average cell voltage being

2 volts and the power density based on the material densities 2000 to 3000 W/kg. For such a $\text{TiO}_2/\text{Li}_y\text{Mn}_2\text{O}_4$ rocking chair thin layer cell configuration power densities of 0.5 to 1.5 $\text{mW cm}^{-2} \mu\text{m}^{-1}$ are observed.

- 5 The mesoporous electrode structure of the said cell configuration and the battery device as a whole also provide for improved local heat dissipation or exchange from the solid during high rate discharge, thus protecting potentially sensitive (active) materials of the battery from degradation, as exposure to extreme temperatures is minimized.

- 10 The mechanical strength is enhanced by controlled sintering process, as the interconnected loops and/or arches are created having a typical aspect ratio of ca. 4, complementing the contribution to the reduction of the system entropy resulting from the natural self-organizing by the templating effect, leading to a structural toughness and robustness of the mesoporous network that can therefore sustain the capillary forces, i.e. not breaking under the intense local pressure when the pores are filled with electrolyte, and most importantly, able to support the strain and mechanical stresses resulting from the volumetric expansion/contraction resulting from the Li^+ insertion/extraction process during the rocking chair battery operation. The later effect induces improved structural integrity on cell cycling, which produces enhanced cyclability as capacity fading due to active material disintegration and discontinuity (decreased electrical connectivity and conductivity) is minimized. Consequently, better solid phase connectivity is ensured with the above mentioned smaller sized "particles" or "grains" or described elemental structural units comprising the mesoporous electrode.

- 25 The preparation according to the preferred embodiment of the invention, results in a crystalline phase that enhances the Li^+ insertion kinetics as long crystalline rows are formed at high temperatures and at short times. The sintered metal oxide layer density (and pore or future anhydrous electrolyte mass vs. oxide mass ratio) can be controlled by solvent (e.g. water) dilution of the oxide precursor and the aggregation state (oxide mass vs. water) of the precursor solution applied.

The full connectivity of the mesoporous space combined with the low tortuosity enables a lower porosity (higher active mass to void (for electrolyte) ratio) to be more effective with respect to the electrolyte function i.e. Li^+ diffusivity.

The two proposed mineral electrodes instead of carbon or lithium metal offer safety in a battery device as the risk of explosion is virtually eliminated in the former case. The battery concept, as of the preferred embodiment of the invention described above, embodies the safety aspect by considering only non-water sensitive and low toxicity materials for electrode fabrication and for the electrolytes as well. Carbon electrode surfaces are very reactive and especially so at high current rates, and require overcharge protection. Also nickel-cobalt oxides are prone to dangerous reactions as well. The manganese oxides are safe in all respects and no charge protection is necessary.

BRIEF DESCRIPTION OF THE DRAWINGS

The features and advantages of the invention are further set out in the following examples, given by way of non-limiting example with reference to the appended drawings in which:

FIG.1 shows a side view of an electrochemical generator of the invention with a partial sector showing the arrangement of the internal layers; (1,2) active material mesoporous electrode layers, (3) the porous separator layer, (4,5) the current collectors.

FIG.2 shows SEM images of the said mesoporous lithium manganate sintered layer under time and conditions set according to a preferred embodiment of the invention.

FIG.3 shows cyclic voltammograms of 1.5 μm layers of the said lithium manganate as a function of treatment temperature.

FIG.4 shows the comparison under shallow cycling of the various types of electrodes under identical potential scan and electrolyte conditions, in order to demonstrate the improved kinetics in the charge/discharge performance of said mesoporous lithium manganate material as a positive electrode.

FIG.5 shows the electrolyte function at steady-state current of the thin layer battery as perceived by the simulation model describing the electrolyte transport behavior of a completely mesoporous cell, by means of the concentration profiles of the Li^+ and the coupling anion species within a multilayer design.

FIG.6 shows examples of electrolytes and their electrochemical properties used in the cell described above.

FIG.7 shows examples of several differently sized $\text{TiO}_2/\text{Li}_y\text{Mn}_2\text{O}_4$ accumulators with respect to current and voltage discharge behavior. All cells utilize pure cellulose paper (30-40 μm (microns)) as the separator.

DETAILED DESCRIPTION OF THE INVENTION

EXAMPLE 1

According to a first embodiment, a secondary electrochemical generator of the "rocking chair" type has $\text{TiO}_2/\text{Li}_y\text{Mn}_2\text{O}_4$ negative and positive electrodes respectively and of the cell configuration depicted in Figure 1. The mesoporous layers are deposited on conducting tin oxide coated glass sheets by the methods previously described. Devices display 20C (or C/0.05) discharge rates under short circuit. The above cell in 30 cm^2 form battery and a thin layer configuration comprising 10 μm (micron) mesoporous layers of the active materials, according to a preferred embodiment, with a separator of pure cellulose paper of 30-40 μm (microns), utilizing electrolyte comprised of methoxypropionitrile and lithium bis-(trifluorosulfonyl) imide, is observed to sustain a 10C (or C/0.1) discharge rate and maintain a cell voltage of 1.5V, resulting in power densities above 1500 W/kg and energy densities above 210 Wh/kg.

EXAMPLE 2

The porosity of a typical sintered layer of the nanosized oxide of an average 8 μm layer estimated by mass to surface measurements reaches as high as 30-70%. Very porous appear to be the layers in the case of 1.5 μm (micron) sintered films treated at 400 and 700 $^\circ\text{C}$, the behavior of which is seen in

Figure 3. The two insertion levels for the spinel in the 4V range reported in the literature (W. Liu et al., J. Electrochem. Soc., Vol.143, No. 3, (1996), 879-884) for 200nm layers at 0.05mV/s, appear very distinct for our 1.5 μm (micron) thickness recorded at a sweep rate over two orders of magnitude higher, demonstrating the higher reversibility in the intercalation kinetics in comparison to the earlier materials, attainable by decreasing the particle size to the nanometer range and simultaneously ensuring effective particle connectivity and mesoporosity. The 700°C material appears to be less resistive and increased electrochemical reversibility and the capacity much higher as compared to the 400°C treatment due to the effective interconnectivity by sintering and material formation at the high temperature, as seen in Figure 2.

EXAMPLE 3

Sintering the primary particles in order to obtain a bicontinuous porous network and thus a high connectivity should therefore be determinant to performance. The idea toward improving the manganates by imparting mesoscopic morphology to a continuous phase i.e. by retaining the connectivity as well as decreasing the primary particle to the nanometer range, significant improvements to the intercalation properties are expected. Making intimate electrical contact within the active mass regardless of size and shape of the oxide, results in enhanced utilization of the oxide and is therefore very desirable. For comparison electrodes are made from the commercial spinel LiMn_2O_4 materials, namely the Selectipur and 5.2 μm (micron) particle powders, both supplied by Merk. The Selectipur particles consist of large hollow spheres (30 μm (micron)) the walls of which appear on SEM to have primary grains of 100-200 μm (microns), extremely tight merged packing; the other appears as a fragmented form of the Selectipur. The pre-formed powders are made into electrodes by mixing the powder with PVA (MW 100000) as binder and graphite particles (Lonza KS-10 or carbon nanotubes) as the conducting matrix. The weight percentage of the constituents are chosen maximum 3% PVA and 10% graphite. The pastes are cast on CTO substrates ambient dried and then heated in an air furnace for 15min at 200 °C. As electrolyte a 1M LiClO_4 in propylene carbonate is the standard in all electrode cycling

experiments to enable objective comparison. Depicted in Figure 4 is the comparison between the Merck powders and a 8 μm (micron) mesoporous layer under shallow cycling of the various types of electrodes under identical potential scan and electrolyte conditions, in order to demonstrate the improved kinetics in the discharge performance of said mesoporous lithium manganate material as a positive electrode. Cyclic voltammetric information elucidates the kinetic aspects of the lithium insertion/extraction in the oxides of the above thin film electrodes. The Selectipur and 5.2 μm (micron) particle electrodes display higher irreversibility than the electrode from the mesoporous material treated at 700 $^{\circ}\text{C}$. as evidenced by the higher induced polarization and discharge peak potential shift toward more negative in the case of the commercial materials. The mesoporous layer shows a clear advantage over the even higher capacity (larger active mass) Selectipur electrode that contains conducting carbon.

EXAMPLE 4

The preferential kinetics are also exemplified by the comparison of the Selectipur 30-40 μm electrode the 8 μm mesoporous layer. In the same voltammetric set up and under a potential scan of 100mV/s a 1.75 to 2 mA/cm² delithiation current at 1.5V vs. AgCl and 7.5 mA/cm², in both cases respectively. At 20mV/s a 1.25 mA/cm² current was measured in the first case and 5 mA/cm² in the second. As another example a 3 μm (micron) LiMn₂O₄ electrode in PC, 1M Li⁺, at short circuit gave a 1.4 mA/cm²/ μm (micron) on charge and discharge. The corresponding value for the delithiation of TiO₂ was 0.4 mA/cm²/ μm (micron). The above Selectipur 30-40 μm electrode gave 0.055 mA/cm²/ μm (micron). Cyclability was the normally expected for the temperature treatment applied and described in the literature. In the glove box, 10% capacity loss was observed within the first 50 cycles at 5 mV/s scan rate and between 1.4 - 2.8V as voltage limits.

EXAMPLE 5

Thin layer cell ionic transport conditions at steady-state are modeled for the mesoporous electrode intercalation cell. The cell configuration consists of two
 5 1millimeter lithium intercalation mesoporous hosts separated by a 20 μm (micron) inert and insulating (meso-)porous spacer, one of the active material layers acting as the insertion and the other as the de-insertion (lithium extraction) electrode. The initial electrolyte concentration in monovalent lithium salt is 1M and the free stream diffusion coefficient for Li^+ in the electrolyte
 10 corresponds to the case of propylene carbonate ($3 \cdot 10^{-6} \text{ cm}^2/\text{s}$) of approximately 3 cP.

In the depicted results of the model the concentration profile of the Li^+ (also the overlapping curve for the anion) appears in Figure 5a and the potential drop across the cell in Figure 5b when approx. $6 \text{ mA}/\text{cm}^2$ are passing through the
 15 cell, the minimum current limiting the supply of Li^+ to one side of the intercalating electrode. The conductivity of the host solid is not considered here. The electrode porosities are 50% and 90% for the separator layer. Anything smaller than 1000 μm (micron) (1mm) would increase the limiting currents. It is noted that the absence of supporting electrolyte in this case aids
 20 the lithium ion diffusion or transport but at a cost of potential in the form of IR drop across the cell (here just under 0.2 V, as depicted in the Figure 5b. This calculation reveals that for electrodes of 10 μm (microns) in the above configuration, currents as high as $500 \text{ mA}/\text{cm}^2$ are possible as far as electrolyte performance is concerned.

25 In addition, the $\text{TiO}_2/\text{cellulose paper}/\text{LiMn}_2\text{O}_4$ cells, with active mesoporous layers of about 10 μm (microns), could deliver more than $5 \text{ mA}/\text{cm}^2$ at short circuit, with molten salts containing 1-2 M lithium - bis (trifluorosulfonyl) imide that has a much higher viscosity ($>40 \text{ cP}$) than in the propylene carbonate case, and thus a lower Li^+ diffusion coefficient.

EXAMPLE 6

From the viewpoint of electrolyte investigation and characterization the sought for properties are generally low viscosity, low volatility, solubility of the lithium salt electrolytes and electrochemical stability/chemical compatibility with the electrode materials. Synthesized are room temperature ionic liquids which have very attractive features in the above respects. The electrochemical stability limits fulfill the requirements for 4V cathode materials, as seen from the examples shown in Figure 6a. The potentials are expressed versus iodide/tri-iodide which is +0.15V vs. AgCl. Di-methyl-ethyl-imidazolium imide offers the best cathodic stability advantages.

Solubility of more than 2M lithium-bis (trifluorosulfonyl) imide can be reached in methoxy-diethoxy propionitrile and in methoxypropionitrile. The electrochemical stability of this newly synthesized organic solvent as evidenced by the electrochemical window is given in Figure 6b. The corresponding stability range for methoxypropionitrile is depicted by the bar in this figure, and the operation limits of the lithium hosts TiO₂ and lithium manganate are positioned against this scale (ferrocene potential is +0.4V vs. AgCl) in Figure 6c.

These molecular structures are designed to exploit the strong solvating properties of the ether groups toward Li⁺, combined with the low viscosity for Li⁺ diffusion and the relatively high boiling points of these compounds to decrease their volatility. Methoxy-ethoxy-propionitrile is also synthesized having viscosity 2.7cP, 1.1cP being for methoxypropionitrile and 5cP for methoxy-diethoxy propionitrile. The boiling points are respectively 240C, 165°C and at 10 mmHg 152°C.

EXAMPLE 7

According to a second embodiment, a secondary electrochemical generator of the "rocking chair" type has TiO₂/Li_{1/2}Mn₂O₄ negative and positive electrodes respectively as described in EXAMPLE 1 and of the cell configuration depicted in Figure 1, however, with the separator layer (3) consisting of a mesoporous zirconia layer of 8 µm (micron) thickness and 60% porous, prepared as described

by P.Bonhote et al., J.Phys.Chem.B. (1998), 102, 1498-1507, displays performance characteristics matching those disclosed in EXAMPLE 1. This mesoporous separator offers advantages for electrolyte penetration in the phase of electrolyte filling of the said electrochemical generator and effective retention
5 of the electrolyte within the mesopores and thus within the generator as a whole, combined with effective displacement of gas from the space of the said generator on electrolyte filling, as well as during operation, that is the effective accommodation of volumetric changes on charge/discharge cycling, allowing for electrolyte movement and gas expulsion from the generator layers(1,2,3) by
10 forced capillary filling of the pores by the liquid electrolyte.

CLAIMS

What we claim is:

1. A high capacity and high power density primary or secondary
 5 electrochemical generator having two electrodes supporting different electroactive materials, said electrodes being connected together by an electrolyte, characterized in that the electroactive material used in the composition of at least one electrode includes an oxide or chalcogenide of transition metals or their lithiated or partially lithiated forms selected
 10 from TiO_2 , Nb_2O_5 , WO_3 , V_2O_5 , MoO_3 , MnO_2 , $\text{Li}_x\text{Mn}_2\text{O}_4$, HfO_2 , TiS_2 , WS_2 , TiSe_2 , Li_xNiO_2 , Li_xCoO_2 , $\text{Li}_x(\text{NiCo})\text{O}_2$, Fe_2O_3 , Fe_3O_4 , RuO_x , Fe_xS_2 , Ru_xS_2 , MoS_2 , WS_2 , Ir_xO_2 , Ce_xO_2 , $\text{Li}_x\text{Na}_y\text{MnO}_z\text{In}$ ($n < 1$), In_xO_3 , Ta_xO_5 , SnM_xO_y , where M is one of glass forming metallic elements or a mixture of these elements, or Sn_xO_2 in mesoporous form having a pore size of 0.001 to 10 μm (micron) and a specific surface area between 2
 15 and 2000 m^2/g .
2. An electrochemical generator according to claim 1 characterized in that the mesoporous electrode is characterized by a three dimensional bicontinuous structure consisting of an interconnected solid phase material used for reversible ion intercalation and for electronic transport which is in contact with an interconnected porous space filled with electrolyte the latter serving for ionic transport, said electrode being characterized by a morphology of the solid phase that is designed to
 20 overcome impediment of ionic diffusion in the electrolyte encountered with conventional high surface area electrodes and a three dimensional structure ascertaining interconnectivity, mechanical stability of the solid phase as well as access of the electrolyte to the entire pore space.
3. An electrochemical generator according to claim 1 or 2 characterized in that the mesoporous electrically active material is prepared by precipitating a precursor compound of said material in aqueous solution via a sol-gel method followed by deposition of the precursor on a
 30

conductive support and sintering at a temperature between 300 and 800 °C.

4. An electrochemical generator according to any of claims 1 to 3
5 characterized in that the mesoporous electrically active material is
prepared by chemical reaction between precursor compounds in
aqueous solution in the presence of surfactant micelles, the said
surfactant micelles acting as templates to produce the desired
mesoporous morphology, particularly in the form of ordered hexagonal
10 arrays.
5. An electrochemical generator according to any of claims 1 to 4
characterized in that the electrically active material is composed of
elongated interconnected members, that are connected to other
15 elongated members in at least two points of an aspect ratio of at least 4
and of which the small dimension of the member is smaller than 300 nm.
6. An electrochemical generator according to any of claims 1 to 5
characterized in that the electrically active material is prepared by
20 inclusion of solvents to the particle or precursor in order to exert control
over the texture and the morphology of the said material and of the
porosity of the electrode, which can be controlled from 70% to 25% by
changing the ratio of oxide precursor grains versus solvent.
7. An electrochemical generator according to any of claims 1 to 6
25 characterized in that the mesoporous electrically active material is
comprised of mesoporous 5-20 μm (micron) beads or rods which are
electrically connected together by compressing in the form of pellets of
films a mixture composed of said beads or rods, of carbon powder or
30 conducting polymer or other matrix and of a bonding material contained
in solvent, then drying said mixture on a conducting support and/or
baking at temperature and long enough time for binder or conductive
matrix conversion to desired state.

8. An electrochemical generator according to any of claims 1 to 8 characterized in that the electrolyte contains alkali or alkaline earth metals in cationic form.
- 5 9. An electrochemical generator according to any of claims 1 to 5 or 7 to 8 and claim 6 characterized in that the alkali metal is lithium on the form of one of its salts chosen from tetrafluoroborate, hexafluorophosphate, hexafluoroantimonate, hexafluoroarsenate, trifluoromethane sulfonate, bis-(trifluorosulfonyl) imide, tris-(trifluorosulfonyl)methide, trifluoro-
10 methanesulfonate, trifluoroacetate, tetrachloroaluminate or perfluorobutane sulfonate.
10. An electrochemical generator according to any of claims 1 to 9, characterized in that the electrolyte includes and aprotic solvent selected
15 from ethylene carbonate, propylene carbonate, dimethylcarbonate, diethylcarbonate, dioxolane, butyrolactone, methoxypropionitrile, methoxy-ethoxy propionitrile, methoxy-diethoxypropionitrile, methoxyacetonitrile, tetrafluoro-propanol or mixtures of these solvents.
- 20 11. An electrochemical generator according to any of claims 1 to 10 characterized in that the electrolyte includes a molten salt as a solvent for the lithium ion containing salt, such as methyl-ethyl-imidazolium trifluoromethanesulfonate, methy-ethyl-imidazolium bis (trifluorosulfonyl) imide or alkylguanidinium bis (trifluorosulfonyl) imide.
- 25 12. An electrochemical generator according to any of claims 1 to 11, characterized in that the electrically active material of one electrode or of each of the two electrodes, is capable of forming an intercalation compound with the alkali or alkaline earth metal.
- 30 13. An electrochemical generator according to any of claims 1 to 12, characterized in that the electrically active material of one electrode is composed of TiO₂ in anatase form having a mesoporous structure.

14. An electrochemical generator according to any of claims 1 to 13,
characterized in that the negative electrode includes mesoporous TiO_2
and the composition of the positive electrode includes $\text{Li}_y\text{Mn}_2\text{O}_4$ ($y < 2$)
in amorphous or crystalline form, the electrolyte being composed of a 1M
solution of lithium bis-(trifluorosulfonyl) imide in methoxypropionitrile as a
solvent.
15. An electrochemical generator according to any of claims 1 to 14,
characterized in that the mesoporous electrically active material
comprised of mesoporous 5-20 μm (micron) beads or rods form an
electrode by templated ordering, manipulative stacking or arrangement
of the said 5-20 μm (micron) secondary mesoporous particles in a
manner that controls particle orientation, the secondary porosity and the
said particle electrical contact by means of an additive conducting matrix
or by treatment (chemical, temperature, external energy field such as
ultrasonic, electromagnetic) of the conducting additive or its precursor or
of the template itself in order to form the conductive phase.
16. An electrochemical generator according to any of claims 1 to 12 or 14 to
15, and claim 13, characterized in that separator (3) is a porous or
mesoporous, high porosity insulating material such as ceramic (zirconia,
alumina) or glass or polypropylene, the above in the forms of continuous
layers or particle spacers and the current collector-substrate (4,5) is
taken from options such as carbon, graphite paper, stainless steel,
titanium or aluminium alloy, DSA, or consist of the conductive matrix
incorporated for conductivity enhancement. Also, characterized in that a
distributed within the active mass or dendritic conductive collector of the
above is used.

ABSTRACT

A high power density and high capacity primary or secondary electrochemical generator in which at least one electrode (1,2) is composed of an electrically active solid material, said electrode having a mesoporous texture forming a bicontinuous junction of large specific surface area with the electrolyte. The specific morphology of the electro-active material permits high rates of ion insertion in the solid while allowing for rapid ion transport in electrolyte present in the porous space of the electrode. Specific methods for preparation of said electrode are disclosed, in particular the control of the electrode morphology by use of surfactant assemblies exerting a templating effect during the chemical synthesis of said electro-active material.

(FIG 1)






Fig. 1

Fig. 2






Fig.4




Fig.5a





Fig.5b



7/11

Fig.6a




Fig.6b




Fig.6c






Fig.7a



11/11

Fig.7b



Please type a plus sign (+) inside this box → ☐

Approved for use through 9/30/00. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63)

☐ Declaration Submitted with Initial Filing ☐ OR ☐ Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)

Attorney Docket Number

First Named Inventor

COMPLETE IF KNOWN

Application Number

Filing Date

Group Art Unit

Examiner Name

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

PRIMARY OR SECONDARY ELECTROCHEMICAL GENERATOR

the specification of which (Title of the Invention)

☐ is attached hereto

OR

☐ was filed on (MM/DD/YYYY) 05.08.1999 as United States Application Number or PCT International

Application Number [PCT/EP99/03261] and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
			YES	NO	
EP 98810431.1	Europe	05.12.1998	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under 35 U.S.C. 119(a) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	
		<input type="checkbox"/> Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

(Page 1 of 2)

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Please type a plus sign (+) inside this box → ☐PTO/SB/01 (12-97)
Approved for use through 9/30/00. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under 35 U.S.C. 120 of any United States application(s), or 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT international application in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application or PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: ☐ Customer Number ☐ OR ☒ Registered practitioner(s) name/registration number listed below

Name	Registration Number	Name	Registration Number
J. Georg Seka	24,491	Chun-Pok Leung	41,405
James F. Hann	29,719		
Charles E. Krueger	30,077		
Kevin T. LeMond	35,933		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet PTO/SB/02C attached hereto.

Direct all correspondence to: ☐ Customer Number or Bar Code Label ☐ OR ☐ Correspondence address below

Name	J. Georg Seka				
Address	Townsend and Townsend and Crew LLP				
Address	Two Embarcadero Center, 8th Fl.				
City	San Francisco	State	CA	ZIP	94111
Country	US	Telephone	415-576-0200	Fax	415-576-0300

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor: ☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))	Family Name or Surname

Inventor's Signature	Date
Residence: City	State Country Citizenship
Post Office Address	
Post Office Address	
City	State ZIP Country

☐ Additional inventors are being named on the _____ supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto

Please type a plus sign (+) inside this box → ☐

Approved for use through 9/30/98. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

PTO/SB/02A (3-97)

DECLARATION

ADDITIONAL INVENTOR(S)
Supplemental Sheet
Page ___ of ___

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))

Family Name or Surname

Michel

Grätzel, Prof. Dr.

Inventor's
Signature

Date

10/26/00

Residence: City

St. Sulpice

State

Country

Switzerland

Citizenship

GERMAN

Post Office Address

Chemin du Marquisat 7a

Post Office Address

CH-1025 St. Sulpice / Switzerland

City

State

ZIP

Country

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))

Family Name or Surname

François R.

Sugnaux, Dr.

Inventor's
Signature

Date

10/26/00

Residence: City

Blonay

State

Country

Switzerland

Citizenship

Swiss

Post Office Address

Chemin du Taux 9

Post Office Address

CH - 1807 Blonay / Switzerland

City

State

ZIP

Country

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))

Family Name or Surname

Nicolas

Pappas, Dr.

Inventor's
Signature

Date

10/26/00

Residence: City

Ecublens

State

Country

Switzerland

Citizenship

Australian

Post Office Address

Chemin de Veilloud, 10

Post Office Address

CH - 1014 Ecublens / Switzerland

City

State

ZIP

Country

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.